



Description

Decortek is a decorative finish made of charges and additives that permit to achieve a pleasant antique wall effect.

Recommended For

Interior applications on plaster, embossed wall coverings, gypsum board, concrete, cement rendering, brickwork & block work.

Key Features

- Resistant to shocks and abrasion
- Water based
- Easy to apply
- Wide range of color combinations

Physical Properties

| | |
|--------------------|--|
| Solvent Type | Waterborne |
| Finish Type | Matt finish based on ASTM D523 |
| Spreading Rate | Approximately 7-8 m ² /kg/coat - 1 coat required |
| Average Dry Time | 3 - 4 hours based on ASTM D 1640 |
| Recoat | 24 - 36 hours |
| Flash Point | None |
| Dry Film Thickness | Up to 50 - 100 microns, depending on application technique |
| Thinner | No thinning required |
| Adhesion | Classified 4B based on ASTM 3359-B for excellent adhesion |
| Scrub Resistance | >4,000 cycles based on EN 13300, formally DIN 53778S |
| Density | 1.02 g/cm ³ |
| VOC | Very low VOC content - Compliant with EU 2010 regulations maximum of 30 g/L. |
| Bases | 1 base: White 800/00 |
| Additives | Colortek Deco Additives (1,2,3, 4,5,6,7,8,9,10), Metallo Roman Silver, Metallo Gold and DB Flake |

Surface Preparation

All surfaces must be cured, clean, dry, and free from dirt, dust, rust, stains, grease, oil, mildew, wax, efflorescence, bond-breakers, and other contaminants. Remove all loose, peeling, or chalky paint by sanding, scraping, or other appropriate methods. Repair all cracks, holes, and other surface imperfections with a suitable patching material. Repaired surfaces should then be sanded smooth and dusted clean. When required prime the surface with a suitable Colortek primer.

New plaster or masonry surfaces must be allowed to cure (28 days) before applying base coat. Cured plaster should be hard, have a slight sheen and maximum pH of 10; soft, porous or powdery plaster indicates improper cure. Never sand a plaster surface; knife off any protrusions and prime plaster before and after applying patching compound. Poured or pre-cast concrete with a very smooth surface should be etched or abraded to promote adhesion, after removing all form release agents and curing compounds. Remove any powder or loose particles.

CAUTION: Scraping or sanding surfaces of older buildings (especially pre-1978) may release dust containing lead or asbestos. **EXPOSURE TO LEAD OR ASBESTOS CAN BE VERY HAZARDOUS TO YOUR HEALTH.** Always wear appropriate personal protective equipment during surface preparation, and finish cleanup of any residues by water-washing all surfaces.



Primer Systems

| SURFACE TYPE | RECOMMENDED COLORTEK PRIMER |
|--------------------|--|
| Drywall | Colortek Primer |
| Porous Masonry | Colortek Sealer, Colortek Primer |
| Non-Porous Masonry | Colortek Primer or Colortek Undercoat |
| Wood | Colortek Undercoat or Colortek Wood Primer |
| Metal | Colortek Adhero, Adhero Quick Dry, SX47 StopRust, AquaZinc |

Application Conditions

Do not apply at temperatures below 5 °C or when rain is expected.

Application Method

Apply Decortek with a brush using crisscross strokes. Then create the effect by smoothing the surface with a plastic spatula 10 to 15 minutes after application.

Pack Size

- 1 US Quart – 1 kg
- 1 US Gallon – 2.5 kg

Shelf Life

24 months from the date of production.

Storage and Handling

Care should be taken to avoid spillage. Store in a dry area. Protect from freezing. Extreme temperatures may cause paint to become unusable. For example: freezing and thawing may cause paint to gel, and high heat may cause solid skin to form.

Safety

Use under well ventilated conditions. Do not breathe or inhale spray mist or sanding dust. Avoid skin contact; spillage on the skin should immediately be removed with suitable cleanser, soap and water. In case of eye contact, flush immediately with water for at least 15 minutes and seek medical attention immediately. If you experience difficulty breathing, leave the area to obtain fresh air. If continued difficulty is experienced, get medical attention immediately.

Cleaning

Remove as much leftover product as possible from the application equipment before cleaning. Clean equipment immediately after use with warm soapy water and rinse thoroughly. Do not empty product into drains or watercourses.

Technical Assistance

Available through your local COLORTEK® Design Center or through your COLORTEK PAINTS® authorized distributor. For the location of the retailer nearest you, email us at info@colortek.eu or check our website www.colortek.eu.

Disclaimer

Product batches are subject to stringent quality control checks in conformity with ISO 9001:2008, Certificate CH12/1128. The information submitted in this manual is correct to the best of our knowledge & experience. No liability whatsoever can be accepted on the basis of the information supplied herein.